



Self-levelling and smoothing compound

- Suitable for locations requiring finished floor surface ready to receive top flooring
- For fine smoothing and levelling substrates
- For interior use
- For renovation and new build
- Foot traffic after 2 – 4 hours
- Excellent flow properties in thin layers
- Thickness: 2-30 mm

Product

Grey, fast-setting, polymer modified powder on the basis of aluminous cement. Applicable by trowel or pump.

Coverage

Approx. 1.7 kg per m² /mm thickness.

Packaging

Available in 20 kg PE lined paper bags.

Surfaces

Concrete subfloors, max humidity 95% RH. Cohesive strength should be min. 1 N/mm². Anhydrite screeds, max. 0.5% residual moisture. Ceramic tiles, terrazzo, and timber floors. For further information and details, please contact our Technical Services Dept.

Surface preparation

The surface should be dimensionally stable, sound, clean and free from dust and laitance. Residues from grease or soap can be removed with Alfix Deep Cleaner. To remove laitance or roughen smooth surfaces, use mechanical preparation, such as sanding or grinding, and vacuum subsequently. For absorbent surfaces, such as concrete, dilute Alfix PlaneMixPrimer with clean water in the ratio 1:3. For smooth or dense substrates, wash/brush the surface using a mixture of Alfix PlaneMixPrimer and levelling powder in the ratio 1:2. Ensure a room temperature of min. +10°C while working. Allow primer to dry before commencing further treatment. Application of smoothing compound should be made within 24 hours after priming. Use self-adhesive foam tape to retain at doors, around floor drains, etc. If possible prevent compound from obtaining contact to walls. For thicknesses exceeding 5 mm, always apply self-adhesive foam tape for walls. Should levelling imply several layers, priming before each new application is required.

Mixing and levelling

Add 3.6 - 4.4 litres of clean cold water per 20 kg bag of powder. Pour water into a clean container and sprinkle in powder while stirring continuously. If possible, use large mixing container or drum for more bags at a time and mix until a lump-free, easy-flowing mix is obtained. Mixing time is approx. 2 minutes using rotary drill paddle. Pour or pump Alfix PlaneMix 30 onto the prepared substrate and spread with notched or straight trowel until the compound flows together into a smooth and even surface. Concrete, min. thickness: 2 mm
Exposure to chair castors, min. thickness: 4 mm
Timber floors, min. thickness: 10 mm

NB!

Additional water should not be added to levelling compound already starting to set.


Note that the temperature of mixing water will influence working time/pot life. Over dosage of water will reduce strength and may produce laitance. Protect from draughts, direct sunlight, and heat. Close broken packaging carefully after use and use the rest within the shortest possible time.

Flooring

Prior to further installation, make sure that the relative humidity on location corresponds to the floor covering in question. Curing rate is influenced by temperature, humidity, ventilation, as well as sub-floor construction.

Tiling: 24 hours at +20°C for layers of up to 3 mm thickness and 7 days for layers of 30 mm thickness. Dense coverings: directional curing time: approx. 3 days at +20°C for layers of 3 mm thickness obtaining 85% RH and 7-21 days for layers of 30 mm.

Precautions

	Alfix A/S H.C. Ørstedes Vej 11-13 DK-6000 Kolding alfix.com 14	Declaration of performance No. 31	DS/EN 13813 CT-C25-F6 Alfix PlaneMix 30 Cementitious screed material for use internally in buildings.
Reaction to fire	A1 _n	Release of corrosive substances	CT
Water permeability	NPD	Water vapour permeability	NPD
Compressive strength	C25	Flexural strength	F6
Wear resistance	NPD	Sound insulation	NPD
Sound absorption	NPD	Thermal resistance	NPD
Chemical resistance	NPD		

Cleaning

Tools and tiles should be cleaned with water before the compound sets.

Cement-based products harden when mixed with water, hence do not pour surplus PlaneMix into the drain system.

Test

Low emission, GEV-EMICODE EC1 - test defined by the German institute Gemeinschaft Emissionskontrollierte Verlegestoffe.

Technical enquiries

Levelling compounds - plane, smooth surfaces with Alfix

Wet rooms – Tanking with Alfix

Product info on:

- Alfix Deep Cleaner
- Alfix PlaneMixPrimer

Product health and safety data /COSH

For further information, please consult our Technical Services Dept.
For latest update of this product info, visit www.alfix.com.

Technical data

Working temperature	+10°C - +25°C
Density	2.0 kg/litre (mixed with water)
Flow EN 12706	Approx. 135-145 mm
Working time	Approx. 20 - 30 minutes at +20°C
Foot traffic	After 2 - 4 hours at +20°C
Flooring:	
- Tiling	After 1 - 7 days at +20°C
- Waterproofing / tiles	After 3 - 7 days at +20°C
- Dense coverings	After 3 - 21 days at +20°C
Full strength	After 28 days at +20°C
Compression strength	25 - 30 N/mm ²
Shelf life	Min. 6 months in unopened bag