



Wide joint grout

- For ceramic wall and floor tiles, rustic and quarry tiles, and natural stone
- For interior and exterior use
- Joints widths: 5 - 20 mm
- Provides a rustic, coarse grained joint

Product

Cement-based powder containing polymer modifiers. Added light stable pigments. Contains quartz sand with grain sizes up to 1.0 mm.

Colours

Available in pale grey and grey
Colour swatches available on request.

Coverage

Tile size / joint width	Coverage per m ²
50 x 50 x 5 mm / 5 mm	approx. 1.9 kg
100 x 100 x 7 mm / 6 mm	approx. 1.7 kg
150 x 150 x 7 mm / 10 mm	approx. 1.9 kg
200 x 200 x 7 mm / 12 mm	approx. 1.7 kg
300 x 300 x 10 mm / 20 mm	approx. 2.6 kg

Packaging

Available in 5 kg and 20 kg PE lined paper bags.

General information

Joints should be clean, dry, and free from loose particles. Joint depth should appear uniform. For grouting with joint width under 5 mm Alfix Cerafill 5 colour or Alfix CeraFill 10 colour is recommended.

Mixing and application

Usually, grouting can be made 48 hours after completion of fixing. Add 0.20 litres of clean water per kg powder. Pour the water into a clean container and add the powder while stirring thoroughly with mixing drill until a lump-free and smooth grout is obtained. Allow the mixture to rest for a few minutes before use.

Apply Alfix CeraFill 20 to the surface with a soft rubber squeegee while working diagonally over the joints ensuring that they are completely filled. Remove excess grout immediately while working.

When the grout begins to set, after approx. 15 – 50 minutes, start to slurry off the area using wet sponge frequently rinsed in clean water. Wipe over tiles in broad sweeps until joints appear even and filled. Finally, clean off and finish tiles and joints with only slightly damp sponge.

Any remaining grout film on the surface can be removed after 12 – 24 hours using an acid cleaner, e.g. Alfix Acid Wash.

NB!

Switch off any underfloor heating.

Note that the temperature of mixing water will influence setting time.

Protect the joints from heat, draught, and other climatic conditions which will cause premature drying. To prevent premature drying, dampen joints for approx. 24 hours in order to obtain complete hardening.

Do not cover areas just grouted with plastic foil or sheets. Avoid any significant changes in temperature or humidity during hardening process.

Variations in drying conditions as well as heavy use of water when cleaning off may affect the cement and cause visible deviations in joint colour.

Cleaning

Grout residues on tiles and tools should be removed with water before the mix begins to set. Cement-based products harden when mixed with water, hence do not pour surplus adhesive into the drain system.

Test

DS/EN 13888

Technical enquiries

Product info on:

- Alfix CeraFill 5 colour
- Alfix CeraFill 10 colour
- Alfix Cleaning and Maintenance products

Product health and safety data /COSH

For further information, please consult our Technical Services Dept.
For latest update of this product info, visit www.alfix.com.

Technical data

Working temperature	+5 °C - +25°C
Density	2.1 kg/litre (mixed with water)
Working time	3 - 4 hours at +20°C
Foot traffic	After 24 hours at +20°C
Full strength	After 14 days at +20°C
Shelf life	Min. 12 months in unopened bags